

Polyethylene Wax

Specification:

Properties	Value	Unit	Standard
Viscosity@140°C	200±50	Cps	ASTMD3236
R&Bsoftening point	105±3	°C	ASTME28
Meltingpoint	100 ±10	°C	DSC
Density	0.90± 0.02	gr/l	ASTMD611
VolatileContent@105°C	<1	%	ASTMD6658
Form	Pastille(<6mm)	-	-
Color	white	-	-

Application:

- Highly effective external lubricant for PVC
- PVC base color and additive masterbatch
- PE and PP base masterbatch
- External lubricant for wood-plastic compound
- Asphalt

Packaging and storage: 25kgPE bag.

It should be stored in a cold and dry place

Tepe Kimya (M) SDN. BHD.

Plo 602 Jalan MIEL 1 Off Jalan Keluli 9
81700 Pasir Gudang Johor MALAYSIA
Tel: +60 7 251 7844 Fax: +60 7 251 7848

Web: www.tepekimya.com

Tepe Kimya San. ve Tic.Ltd.Şti.

Kimyacılar Organize Sanayi Bölgesi
Melek Aras Bulvarı N:12 34959
Tepeören Tuzla İstanbul/TURKEY
Tel:+90 216 5931920 Fax:+90 216 5931925

Tepe Trade Intl. Chem Pte. Ltd.

63 Mount Sinai Drive #05-01
277116 SINGAPORE
Tel:+65 932 65813 Fax: +65 631 48 435

Email: info@tepekimya.com